



押出級 ABS, POLYLAC[®] PA-747S

VIW

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PA-747S
引張強度 Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm ² (lb/in ²)	390(5530)
延伸率 Tensile Elongation	ASTM D638	1/8", 6 mm/min	%	40
彎曲強度 Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	620(8800)
彎曲彈性率 Flexural Modulus	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	21000(300000)
IZOD 衝擊強度 Izod Impact Strength	ASTM D256(Notched)	1/4", 23°C	Kg-cm/cm(ft-lb/in)	35(6.5)
		1/8", 23°C	Kg-cm/cm(ft-lb/in)	40(7.5)
流動係數 Melt Flow Index	ASTM D1238	200°C, 5Kg	g/10min	0.7
硬度 Hardness	ASTM D785	1/2"	R Scale	102
比重 Specific Gravity	ASTM D792	23°C	-	1.03
軟化點 Vicat Softening Temp	ASTM D1525	1/8", 50°C /hr	°C (°F)	103(217)
熱變形溫度 H.D.T Annealed(85°C, 8hr) Unannealed	ASTM D648	1/4", 120°C /hr	°C (°F)	97(206)
				87(189)
燃燒率 Flammability	UL 94	-	-	1/16"HB

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000